



DAMPFLEX PRIMER

DESCRIPTION

A solvent based primer used for the priming of surfaces prior to the application of Dampflex waterproofing membrane.

USES

Dampflex Primer can be used over concrete, render, fibre cement and other building board surfaces.

FEATURES AND BENEFITS

- Being solvent-based Dampflex Primer etches the substrate and thus enhances the bond of Dampflex waterproofing membrane onto the surface.
- Being a one-pack primer it is easy to use directly out of the container.

SURFACE PREPARATION

- All surfaces must be dry, clean and free from dirt, dust, oil, grease, wax, paint, curing compounds and all other loose contaminating materials.
- Concrete surfaces must be allowed to cure for six weeks.
- Rendered surfaces must be allowed to cure for at least 7 days.
- All concrete and rendered surfaces must have a woodfloat finish.

APPLICATION

- Apply Dampflex Primer with a brush or roller ensuring that the entire surface is coated.
- Allow the primer 20-30 minutes to dry, depending upon site conditions, prior to applying Dampflex waterproofing membrane.
- Do not pool the primer.

PRECAUTIONS

- Allow adequate ventilation when using Dampflex Primer.
- Dampflex Primer is classified as flammable and thus must be kept away from a naked flame.
- Being hazardous, avoid contact with eyes and skin. It is recommended that applicators wear PVC or similar gloves and safety goggles.

- For a full MSDS contact your ParexDavco (Australia) Pty Ltd state office.

COVERAGE

Approximately 10 m²/L depending upon site conditions.

CLEAN UP

Tools and excess primer can be cleaned up with mineral turps.

PACKAGING

Dampflex Primer is available in 1 litre, 4 litre and 20 litre containers.

SHELF LIFE

Up to 12 months in unopened containers stored in a cool dry place.

TECHNICAL DATA

Properties:

Appearance:	Clear blue liquid
Specific Gravity:	1.0kg/L
Working Time at 20°C:	5-15 minutes
Drying Time at 20°C:	30 minutes

DISCLAIMER

The use of this product is beyond the manufacturer's control, and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. All workmanship must be carried out in accordance with AS 3470 - 1994.

The information contained herein is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for a particular application. Users are asked to check that the literature in their possession is the latest issue.

PAREXDAVCO

ParexDavco (Australia) Pty Limited

ABN 28 098 876 553

67 Elizabeth Street Wetherill Park NSW 2164 Australia

Telephone: 61 2 9616 3000 Facsimile: 61 2 9725 5551

Toll Free Technical Advice Line: 1800 653 347

Email: technical@parexdavco.com.au Website: www.parexdavco.com.au

