



# TRADEFIX WHITE

---

## DESCRIPTION

---

Tradefix White is a white acrylic, based, flexible, pre-mixed, interior, thin bed, wall tile adhesive.

## USES

---

- Tradefix White can only be used for interior wall tiling installations.
- Tradefix White can be used for thin bed fixing of tiles directly onto fibre cement sheeting, plasterboard and rendered walls.
- Tradefix White can be used to fix most types of porous ceramic and marble wall tiles, particularly light coloured marbles, but with the exception of green marble.
- When using Tradefix White with translucent/absorbent tiles, the colour of the adhesive must be considered.
- Tradefix White must not be used on floors or over waterproofing membranes.

## FEATURES AND BENEFITS

---

- Premixed – ready to use!
- No need for messy mixing making Tradefix White very easy to use.
- White in colour so there is no show through in the grout joint.
- Perfect for bathroom, kitchens and laundry walls.

## SURFACE PREPARATION

---

- All surfaces must be structurally sound, dry, clean and free from movement, oil, grease, wax, curing compounds and any other loose or contaminating materials.
- All building boards must be flat and firmly fixed according to the manufacturer's instructions and relevant Australian Standard(s).
- Painted surfaces must be scabbled/abraded to expose at least 80% of the original substrate.
- Newly rendered surfaces must be allowed to cure for at least 7 days and have a wood float finish.
- Old rendered surfaces must be thoroughly cleaned prior to tiling and have a wood float finish.

- Porous/dusty surfaces must initially be primed using Davco Ultraprime.

### Movement joints should be provided as follows:

1. Over movement joints in the background.
2. At a junction between different background materials
3. At fixtures interrupting the tile surface e.g. columns.
4. At internal vertical corners.
5. Around the perimeter of the tiling system.
6. At a maximum of 5 metre intervals in a grid pattern.

**Note:** Movement joints should go right through the tile and adhesive bed to the background and be kept free from dirt and adhesive droppings. Movement joints should not be less than 6mm wide nor greater than 10mm wide. Movement joints that are 6mm wide can be filled with Davco *Sanitized*<sup>®</sup> Colorcaulk. For wider applications use Davco Davsil polysulphide or polyurethane type fillers.

## APPLICATION

---

- Spread the adhesive onto the substrate using a 6mm x 6mm notched trowel for installation of tiles up to 150mm x 150mm.
- For the installation of tiles larger than 150mm x 150mm use a 10mm x 10mm notched trowel.
- Tiles with lugs, grooves or an uneven back must initially be butter coated with the adhesive, in addition to the adhesive being trowelled onto the substrate.
- For mosaic tiles, use a 6mm x 6mm-notched trowel.
- A minimum final bed thickness of 2mm is recommended, but the final bed thickness must not exceed 4mm.
- Do not spread more than 0.5m<sup>2</sup> of adhesive at one time.
- Press tiles firmly into position before the adhesive skins, ensuring that all the tiles are well bedded and that no voids occur under the tiles.
- Occasionally, in order to ensure that full coverage is being maintained, a tile should be removed, the adhesive coverage noted and the tile be relaid accordingly.
- Once the tiles have been laid, they must not be disturbed for 24 hours at 20°C.



# TRADEFIX WHITE

## GROUTING

- Grouting can be carried out 24 hours after the completion of tiling.
- Use the Davco grout that best suits the tiling installation. Refer to the Davco Adhesive and Grout Selection Guide for further information.
- To enhance colour, increase water resistance and flexibility of the grout, use Davco Grout Additive. This is particularly recommended when grouting over timber or fibre cement sheeted floors, to minimise the likelihood of the grout cracking/powdering.
- Allow 24 hours after grouting before putting the area into service.

## PRECAUTIONS

- Do not apply Tradefix White in temperatures above 40°C or below 5°C.
- Do not allow the adhesive to skin prior to laying the tiles. If the adhesive skins, remove and dispose of it, then re-apply fresh adhesive.
- Do not use Tradefix White over impervious surfaces (i.e. waterproofing membranes) or to bond low porosity tiles.
- Tradefix White is not suitable for fixing tiles externally or onto floors.
- Tradefix White is not suitable for the tiling of areas where continual dampness/immersion occurs, such as shower recess bases, swimming pools, spas, etc.
- For a full MSDS on this product, contact your ParexDavco (Australia) Pty Ltd state office.

## COVERAGE

One litre of Tradefix White covers approximately 0.75m<sup>2</sup> using a 6mm x 6mm notched trowel.

## CLEAN UP

- Remove any excess adhesive from the face of the tiles with a damp cloth, while the adhesive is still wet.
- Clean tools and equipment with water before the adhesive dries.

## PACKAGING

Tradefix White is available in 15 and 20 litre containers.

## SHELF LIFE

Tradefix White in unopened containers, has a shelf life of up to 12 months, stored in a cool, dry place.

## TECHNICAL DATA

Properties:	White Paste
Appearance:	White Paste
Specific Gravity:	1.65 kg/litre
Open Time at 20°C:	5 minutes
Adjustment Time at 20°C:	15 minutes
Curing Time at 20°C:	24 hours

## DISCLAIMER

*The use of this product is beyond the manufacturer's control, and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. All workmanship must be carried out in accordance with AS 3958.1 - 1991.*

*The information contained herein is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for a particular application. Users are asked to check that the literature in their possession is the latest issue.*

## PAREX DAVCO

**ParexDavco (Australia) Pty Limited**

ABN 28 093 876 558

67 Elizabeth Street Wetherill Park NSW 2164 Australia

Telephone: 61 2 9616 3000 Facsimile: 61 2 9725 5551

Toll Free Technical Advice Line: 1800 653 347

Email: [technical@parexdavco.com.au](mailto:technical@parexdavco.com.au) Website: [www.parexdavco.com.au](http://www.parexdavco.com.au)

